

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problems Mailbox.**

THIS PAGE BLANK (USPTO)

cited in the European Search
Report of EP 01 12 8335.5
Your Ref.: TS-369-EP-DE 8



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: H01L 21/306	A1	(11) International Publication Number: WO 95/04372 (43) International Publication Date: 9 February 1995 (09.02.95)
(21) International Application Number: PCT/US94/07943 (22) International Filing Date: 15 July 1994 (15.07.94) (30) Priority Data: 08/100,537 30 July 1993 (30.07.93) US (71) Applicant (for all designated States except US): SEMITOOL, INC. [US/US]; 655 West Reserve Drive, Kalispell, MT 59901 (US). (72) Inventor; and (75) Inventor/Applicant (for US only): JOLLEY, Michael, K. [US/US]; 115 East Bluegrass Way, Kalispell, MT 59901 (US). (74) Agents: GREGORY, Randy, A. et al.; Suite 815, 601 West Main Avenue, Spokane, WA 99201-0679 (US).		(81) Designated States: AT, AT (Utility model), AU, BB, BG, BR, BY, CA, CH, CN, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), ES, FI, FI (Utility model), GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, SK (Utility model), TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD). Published <i>With international search report.</i>
(54) Title: METHODS FOR PROCESSING SEMICONDUCTORS TO REDUCE SURFACE PARTICLES (57) Abstract Methods for removing particulates from the surfaces of semiconductor materials, such as silicon substrates and wafers. The methods use repeated oxide growth steps and intervening oxide removal. Rinses are preferably used between the oxide growth and removal steps, such as with purified water. The oxide growth steps use an oxidation agent and a base, for example hydrogen peroxide and ammonium hydroxide. The oxide removal steps use a suitable oxide removal agent such as a hydrogen halide acid, for example hydrogen fluoride. The oxide removal steps are limited so that some oxide remains to thus maintain a hydrophilic wafer surface.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

DESCRIPTION
**METHODS FOR PROCESSING SEMICONDUCTORS
TO REDUCE SURFACE PARTICLES**

Technical Field

5 This invention relates to processes for cleaning semiconductor materials to reduce the presence of contaminating materials present on the surfaces of these materials.

Background Art

10 The production of semiconductors into various types of integrated circuits, displays, memories, sensors and other devices typically requires that contaminating particles be minimized. In many cases the presence of contaminating particles can cause defective operation, performance problems, or render the device inoperable.

15 It has previously been typical for silicon wafers to be processed using a method commonly referred to as the "RCA clean". In this process the silicon wafer, substrate, or other item is first cleaned with an aqueous solution of sulfuric acid and hydrogen peroxide to remove organic contaminants. This is followed by treatment with an aqueous solution of ammonium hydroxide and hydrogen peroxide. After this the wafers are rinsed with deionized water.

20 The RCA clean also typically involves stripping the silicon dioxide layer formed in the previous steps using an aqueous hydrofluoric acid solution. The hydrofluoric acid solution removes the silicon dioxide layer leaving bare silicon. The bare silicon demonstrates the property of not being easily wetted and is frequently referred to as being "hydrophobic". This should be contrasted with the
25 silicon dioxide surface existing prior to this step, which is easily wetted and the wafer is commonly called "hydrophilic".

 The hydrofluoric acid oxide removal step is typically followed by a short rinse in deionized water. The rinse is kept short to minimize silicon dioxide formation. The rinsed wafer is typically not dried.

30 The RCA clean method also typically includes transferring the wet wafer from the previous step into an aqueous solution of hydrochloric acid and hydrogen peroxide. This step is designed to dissolve metals.

 Although this sequence of processing steps is widely used, it is recognized that the process is of limited effectiveness for removing surface adhering particles.
35 The effectiveness is limited to a certain level of particle contamination dependent

upon prior processing and the level of cleanliness existing on the wafer when the cleaning process is begun.

The cleaning of semiconductor surfaces has great economic significance because of the volume of integrated circuits and other semiconductor devices being produced, and the significant percentage of processed semiconductor devices which are rejected due to defects caused by particle contamination. Particle contamination is also of great significance because of increased facilities and equipment cost, and costly and time-consuming procedures used in an effort to prevent particle contamination. It is generally recognized that contamination must be prevented because it is often difficult or impossible to adequately remove contaminants once contamination has occurred.

Thus there has long remained a need for improved cleaning processes which are effective at removing particulate contaminants from the surface of silicon and other semiconductor materials.

Best Modes for Carrying Out the Invention and Disclosure of Invention

Methods according to this invention include repeated treatment of a semiconductor surface with an oxidation agent and a base. The oxidation agent and base are preferably presented combined together in a liquid mixture or solution with a diluent. The diluent is preferably a solvent diluent, most preferably purified water.

Examples of suitable oxidation agents include a suitable peroxide, such as hydrogen peroxide (H_2O_2). The oxidation agent or agents are preferably in solution with a suitable diluent, preferably a suitable solvent, such as purified water. An alternative oxidation agent is ozone. The ozone can be bubbled into a purified solvent diluent, preferably purified water, to achieve an ozonized water oxidizing agent. The concentration of the ozone is preferably at the saturation point for the desired processing temperatures.

The oxidation agent is provided in a suitable concentration to achieve a rate of oxidation which provides oxide layer growth of the desired amount for the processing conditions and time being used. In the preferred oxidation agent-base mixture, hydrogen peroxide can be present in quantities sufficient to provide molar ratios in the range of approximately 5:2 to approximately 50:1, more preferably approximately 5:1 to 10:1, even more preferably approximately 5:1 (water:hydrogen peroxide).

The preferred mixture or solution containing the oxidation agent also includes a suitable base. The base is believed to provide solubilizing properties

and create similar electrostatic charge conditions on particles and the semiconductor surface which cause the particles to be repelled and reducing the risk of particle reattachment. The base is advantageously a hydroxide. The base is preferably selected from the group consisting of ammonium hydroxide
5 (NH₄OH), sodium hydroxide (NaOH), potassium hydroxide (KOH), and quaternary ammonium compounds, such as choline (C₅H₁₄NO⁺), and tetramethylammonium hydroxide ((CH₃)₄NOH).

The base or bases which are included in the oxidation agent-base mixture are preferably provided in sufficient amounts to provide a pH in the approximate
10 range 7.001 to 14. For the most preferred base, ammonium hydroxide, and other bases of similar activity, the base is advantageously included in molar ratio relative to the preferred diluent solvent water to provide ranges of approximately 500:1 to 5:2, more preferably 100:1 to 5:1, most preferably 20:1 (water:ammonium hydroxide).

15 The concentration of the base is also related to the concentration of the oxidation agent. The oxidation agent provides cleaning properties and promotes oxidation of the semiconductor surface. If the base acts as an etchant, such as ammonium hydroxide does against silicon, then the oxidation agent must be in sufficient concentration to provide an oxidation rate of the semiconductor material
20 which produces a net growth rate against the rate of etching caused by the base. In the preferred oxidation agent-base mixtures for silicon comprising water, hydrogen peroxide, and ammonium hydroxide, the ratios are in the range of approximately 10:1:1 to approximately 100:1:0.1.

The novel methods of this invention also preferably comprise one or more
25 steps wherein the oxide coated surface of the semiconductor material is exposed to an oxide removal agent. The oxide removal agent is selected to be effective against the oxide developed in prior processing. In the preferred case of oxide removal after a prior treatment with the oxidation agent-base mixture, the oxide removal agent is selected to effectively remove the oxide developed by the
30 reaction of the oxidation agent-base mixture upon the semiconductor surface involved.

The oxide removal agent is advantageously selected from the group of hydrogen halide acids. In the case of silicon the preferred oxide removal agent is hydrogen fluoride.

35 The oxide removal agent is preferably presented to the semiconductor surface in the form of a liquid mixture or solution with a suitable diluent, which

is preferably a diluent solvent, such as the preferred purified water. The concentration of the oxide removal agent in the diluent or solvent is determined by the reactivity of the oxide removal agent against the oxide being removed and the need for uniform and repeatable reaction rates. In the preferred methods
5 for treatment of silicon the oxide removal agent is relatively dilute hydrogen fluoride. Concentrations of hydrogen fluoride are preferably in the range of approximately 10,000:1 to 10:1, more preferably approximately 1,000:1 to 100:1, even more preferably 500:1 (water:hydrogen fluoride).

The novel methods according to this invention include repeated treatments
10 with the oxidation agent-base with intervening oxide removal using the oxide removal agent. The oxide removal is preferably done at a rate and for a time sufficient to remove at least half but less than all of the semiconductor oxide layer existing on the surface of the semiconductor material. More preferably the oxide removal agent is used to remove at least two-thirds of the surface oxide
15 layer but less than all. Even more preferably the oxide removal agent step removes between two-thirds and three-fourths of the surface oxide layer.

It is important to recognize that prior art cleaning methods involved taking the entire surface oxide layer from the semiconductor material. In the case of silicon, this caused the surface to become hydrophobic. The novel methods of
20 this invention keep the semiconductor surface in a hydrophilic condition. Thus the oxide removal step should not be allowed to remove all the oxide otherwise the surface will go hydrophobic and the effectiveness of the methods will be significantly depreciated.

The repeated alternating treatments with the oxidizing agent-base and oxide
25 removal agent are preferably separated by intervening or intermediate rinsing steps. These intervening rinsing steps are preferably accomplished using a suitable diluent or solvent, more preferably a solvent which can help to carry away loosened particles. The solvent or other diluent is preferably selected to be a common diluent or solvent present in both the oxidizing agent-base
30 treatments and oxide removal treatments. Most preferably the rinsing is accomplished using purified water. The purified water is preferably deionized water of high resistivity, or distilled and deionized water of high resistivity, such as 10 megohms or greater resistivity. The use of intervening water or other rinses arrests or inhibits the oxidation and effects of the base. The rinses also
35 inhibit or arrest the action of the oxide removal agent when performed after such processing. The rinsing steps are preferably accomplished at room

temperatures, 15-25°C, for periods of approximately 30 seconds to 5 minutes, more preferably 1-3 minutes, even more preferably approximately 2 minutes.

The various processing steps used in the novel processes of this invention are most preferably accomplished within a substantially enclosed processing chamber using liquids of very high purity which are sprayed on the semiconductor surfaces. Most preferably the liquids are sprayed on wafers, substrates or other semiconductor materials which are being rotated or otherwise spun or moved as the liquids are sprayed upon the surfaces. The centrifugal forces developed by the rotating wafers helps to provide uniform and even distribution of the liquids across the entire surface. The spinning action also moves the liquids from the processed surface or surfaces thus better preparing the surface for subsequent processing. Preferred rotation speeds are in the range of approximately 30-3000 rpm, more preferably 30-1,000 rpm, even more preferably 30-600 rpm.

The centrifugal processing also is more convenient in that it allows the repeated alternate processing steps to be preformed numerous times, as desired without intervening handling or drying of the wafers. A preferred centrifugal processing apparatuses for carrying out the novel methods include Semitool models SAT 2080S or SAT5061T, available from Semitool, Inc. of Kalispell, Montana.

Example 1

Twenty five (25) six inch diameter (150mm) silicon wafers were loaded into a wafer holder. The wafers had previously been used for testing and were considered dirty. The wafers suffered from general contamination and room dust accumulations. Testing was being done to reclean the wafers. The wafers thus had some oxide surface layer formed thereon due to the development of silicon oxide from exposure to air.

The wafers were processed in a centrifugal spray processor Semitool model 2080S for all steps except final rinsing and drying which were performed in a spin rinser dryer. The initial oxidation-base treatment was performed in a 5:1:0.25 mixture of water:hydrogen peroxide:ammonium hydroxide at 80°C for periods range between 3-10 minutes. The wafers were spun at speeds of approximately 35 rpm during this step. The mixture returned to the processing fluid tanks for subsequent reuse.

Following the oxidation-base treatment, the wafers were rinsed in deionized water at 20°C for 2 minutes. During the rinse cycle the wafers were spun for a period of 1 minute at 35 rpm, and for an additional 1 minute at 300 rpm.

The rinse cycle was followed by oxide removal using a 500:1
5 water:hydrogen fluoride mixture. The exposure to the oxide removal agent was accomplished at 20°C for 1-2 minutes at rotational speeds of 35 rpm. The mixture was filtered and returned to the processing fluid tanks for subsequent reuse.

The oxide removal processing was followed by another rinse cycle using
10 deionized water as explained above.

After the second rinse the wafers were treated a second time using the same oxidation agent-base aqueous mixture as recited above and under the same operational conditions.

The second treatment with the oxidation agent and base was following by
15 another deionized water rinse cycle as explained above.

After the previous rinse step, a second oxidation removal treatment was performed using the same conditions and processing as explained above for the first oxide removal treatment.

Another deionized water rinse was then performed in the manner
20 explained above.

The wafers were then treated a third time using the same oxidation agent-base and water mixture and processing conditions as explained above.

Thereafter the wafers were rinsed a further time and spun to dry in a nitrogen purged processing chamber at approximately 80°C.

25 Analysis of the processed wafers showed particle count reductions after the above processing of approximately 98% percent removal. The wafers showed average total particle counts of less than 50 particles per wafer for particles of size 0.2 micron or greater after the processing.

30

Example 2

Two (2) previously cleaned wafers having particle counts of less than 100 particles per wafer of size 0.2 micron or larger were further processed using HF to remove all native oxide developed on the wafers since the prior cleaning. The wafers were rinsed and dried and then particle counted again. The
35 resulting wafers demonstrated hydrophobic surfaces and particle counts greatly

higher than the 100 particles per wafer. Specifically, Wafer #1 had 21,083 particles and Wafer #2 had 31,456 particles.

The two hydrophobic wafers were further processed in a manner similar to that explained in Example 1 except that the sequence of oxidation-base treatments, rinses, and oxide removal steps were repeated so that there was a total of four (4) oxidation-base treatments lasting 5 minutes each, and a total of three (3) oxide removal steps lasting 40 seconds each.

After the above processing wafer #1 had 108 particles and wafer #2 had 80 particles.

10

Example 3

Silicon wafers 200 millimeters in diameter were polished using a chemical-abrasive slurry. Removing the slurry is a significant cleaning challenge. The wafers with slurry were first rinsed with deionized water using a centrifugal spray acid processor. This preliminary step was used to remove the excess slurry. The resulting wet wafers were further processed in the same machine using substantially the same sequence as described in Example 1, except the oxidation-base steps were performed for periods of 5 minutes, and the oxide removal steps were performed for periods of 2 minutes 15 seconds. A finish spin rinse and dry were performed in a centrifugal spin rinser dryer.

The processing described above resulted in wafer #1 having particle counts of 31 prior to slurry polishing and 46 after slurry polishing and cleaning using the described process. Wafer #2 had particles counts of 30 before slurry polishing and 22 after slurry polishing and cleaning using the described process.

The cleaning performance described above in this Example must be contrasted with a control group of two wafers which were merely rinsed in the spray acid processor and then rinsed and dried using deionized water in the centrifugal spin rinser dryer. The wafers in this control group had particle counts of 38 and 27 before slurry polishing versus 1220 and 1188, respectively, after slurry polishing and the simple rinsing and drying steps.

Example 4

A modified cleaning process similar to that used on the first group of wafers described in Example 3 was also performed on a third group of two wafers. The process varied in that the initial rinsing step was first followed by the described oxide removal step instead of first using the oxidation-base step.

This starting oxide removal could be employed because the oxide layer from previous processing of the wafers was sufficiently thick to prevent total removal of the oxide layer. Thus the wafer did not turn hydrophobic. Two oxide removal and two oxidation-base processing subroutines were performed with
5 associated intervening rinses as described above.

The wafers processed in this testing demonstrated particle counts of 48 and 22 before slurry polishing versus 25 and 19, respectively, after slurry polishing and the described cleaning process.

10

Example 5

Silicon wafers 200 millimeters in diameter were used for oxide growth uniformity testing. The wafers were initially treated with an oxidation-base step as described in Example 1. Thereafter the wafers were totally stripped of the oxide layer by removing approximately 80 Angstroms of grown oxide using a
15 spray water:HF solution (500:1 water:HF). This stripping operation is typically used to strip oxide to prepare the wafer for subsequent thermal diffusion processing.

The resulting hydrophobic, oxide-stripped wafers were then cleaned using a process similar to that described in Example 1. The oxidation-base steps were
20 performed for 10 minutes, and the oxide removal steps were performed for 1 minute.

The particle counts before cleaning were 670 particles and after the described processing 64 particles.

25 The particle removal mechanisms performed by the novel processes are not understood with certainty. However, it is hypothesized that the oxide growth phase in the presence of a base creates a growing oxide layer which induces substantial compressive film stresses. These compressive film stresses in the growing oxide layer are believed to separate previously attached particles from
30 the surface. The presence of the base in the processing mixture causes the particle and surface of the semiconductor to both be similarly charged. This like charge state is believed to mitigate against subsequent particle reattachment to the surface.

The oxide removal process step is believed to cause oxide removal from
35 about embedded particles and thus leave them mechanically susceptible to being solubilized and rinsed away. Maintaining the wafer surface with at least some

oxide layer maintains the protective oxide over the more adherent bare silicon or other semiconductor material.

Although this explanation is believed accurate, the exact mechanism for the superior cleaning efficacy of the novel methods of this invention are have
s not yet been adequately proven and may occur due to other mechanisms.

Industrial Applicability

The inventions are useful in the cleaning of semiconductor materials, particularly silicon semiconductor wafers.

Claims

1. A method for processing a surface of semiconductor material to remove contaminants therefrom, characterized by:
repeatedly treating the surface by performing alternating growing and
5 removing steps defined as follows:
growing a semiconductor oxide on the surface using a suitable oxidation agent; said growing being performed using a base in combination with said oxidation agent;
removing semiconductor oxide from the surface using an oxide
10 removal agent;
said removing and growing steps being further defined by maintaining a semiconductor oxide layer upon the surface throughout the method.
- 15 2. A method according to claim 1 wherein said removing removes at least half and less than all of an oxide layer existing on the surface.
3. A method according to claim 1 wherein said removing removes at least two-thirds and less than all of an oxide layer existing on the surface.
- 20 4. A method according to claim 1 wherein said removing removes in the range of approximately two-thirds to three-fourths of an oxide layer existing on the surface.
- 25 5. A method according to claim 1 and further comprising rotating the surface while said growing or removing steps are performed.
6. A method according to claim 1 and further comprising rotating the surface while liquids are sprayed onto the surface.
- 30 7. A method according to claim 1 wherein said oxidation agent, base, and oxide removal agent are liquids sprayed onto the surface.
8. A method according to claim 1 wherein said oxidation agent, base,
35 and oxide removal agent are liquids sprayed onto the surface; and further comprising rotating the surface while said liquids are sprayed onto the surface.

9. A method according to claim 1 wherein said oxidation agent, base, and oxide removal agent are liquids sprayed onto the surface; and further comprising rotating the surface within a substantially enclosed processing chamber while said liquids are sprayed onto the surface.

5

10. A method according to claim 1 wherein said oxidation agent includes at least one constituent selected from the group consisting of hydrogen peroxide and ozone.

10 11. A method according to claim 1 wherein said oxidation agent includes at least one peroxide.

12. A method according to claim 1 wherein said oxidation agent includes hydrogen peroxide.

15

13. A method according to claim 1 wherein said oxidation agent includes hydrogen peroxide in an aqueous solution in the range of approximately 5:2 to approximately 50:1 (water:hydrogen peroxide).

20 14. A method according to claim 1 wherein said base includes at least one hydroxide.

15. A method according to claim 1 wherein said base includes ammonium hydroxide.

25

16. A method according to claim 1 wherein said base includes at least one selected from the group consisting of: ammonium hydroxide, sodium hydroxide, choline, tetramethylammonium hydroxide, and other quaternary ammonium compounds.

30

17. A method according to claim 1 wherein said base includes ammonium hydroxide in an aqueous solution in the range of approximately 5:1 to approximately 100:1 (water:ammonium hydroxide).

35 18. A method according to claim 1 wherein said oxidation agent includes hydrogen peroxide, and said base includes ammonium hydroxide.

19. A method according to claim 1 wherein said oxidation agent includes hydrogen peroxide in an aqueous solution in the range of approximately 5:2 to 50:1 (water:hydrogen peroxide), and said base includes ammonium hydroxide in an aqueous solution in the range of approximately 5:1 to 5 approximately 100:1 (water:ammonium hydroxide).

20. A method according to claim 1 wherein said oxidation agent includes hydrogen peroxide in an aqueous solution in the range of approximately 5:2 to 50:1 (water:hydrogen peroxide), and said base includes ammonium hydroxide in an aqueous solution in the range of approximately 5:1 to approximately 100:1 (water:ammonium hydroxide); said oxidation agent, base, and oxide removal agent are liquids sprayed onto the surface; and further comprising rotating the surface while said liquids are sprayed onto the surface.

21. A method according to claim 1 wherein said oxide removal agent includes an aqueous hydrogen halide.

22. A method according to claim 1 wherein said oxide removal agent includes hydrogen fluoride.

23. A method according to claim 1 wherein said oxide removal agent includes hydrogen fluoride in an aqueous solution in the range of approximately 10:1 to 10,000:1 (water:hydrogen fluoride).

24. A method according to claim 1 wherein said oxide removal agent includes hydrogen fluoride in an aqueous solution in the range of approximately 100:1 to 1,000:1 (water:hydrogen fluoride).

25. A method for processing a surface of semiconductor material to remove contaminants therefrom, characterized by:

repeatedly treating the surface by performing alternating growing and removing steps defined as follows:

5 growing a semiconductor oxide on the surface using a suitable oxidation agent; said growing being performed using a base in combination with said oxidation agent;

 rinsing the surface to inhibit activity of the oxidation agent and base;

10 removing semiconductor oxide from the surface using an oxide removal agent;

 rinsing the surface to inhibit activity of the oxide removal agent;

 said removing and growing steps being further defined by maintaining a semiconductor oxide layer upon the surface throughout the
15 method.

26. A method according to claim 25 wherein said removing removes at least half and less than all of an oxide layer existing on the surface.

20 27. A method according to claim 25 wherein said removing removes at least two-thirds and less than all of an oxide layer existing on the surface.

 28. A method according to claim 25 wherein said removing removes in the range of approximately two-thirds to three-fourths of an oxide layer existing
25 on the surface.

29. A method according to claim 25 and further comprising rotating the surface while said growing or removing steps are performed.

30 30. A method according to claim 25 and further comprising rotating the surface while liquids are sprayed onto the surface.

31. A method according to claim 25 wherein said oxidation agent, base, and oxide removal agent are liquids sprayed onto the surface.

32. A method according to claim 25 wherein said oxidation agent, base, and oxide removal agent are liquids sprayed onto the surface; and further comprising rotating the surface while said liquids are sprayed onto the surface.

5 33. A method according to claim 25 wherein said oxidation agent, base, and oxide removal agent are liquids sprayed onto the surface; and further comprising rotating the surface within a substantially enclosed processing chamber while said liquids are sprayed onto the surface.

10 34. A method according to claim 25 wherein said oxidation agent includes at least one constituent selected from the group consisting of hydrogen peroxide and ozone.

15 35. A method according to claim 25 wherein said oxidation agent includes at least one peroxide.

36. A method according to claim 25 wherein said oxidation agent includes hydrogen peroxide.

20 37. A method according to claim 25 wherein said oxidation agent includes hydrogen peroxide in an aqueous solution in the range of approximately 5:2 to approximately 50:1 (water:hydrogen peroxide).

25 38. A method according to claim 25 wherein said base includes at least one hydroxide.

39. A method according to claim 25 wherein said base includes ammonium hydroxide.

30 40. A method according to claim 25 wherein said base includes at least one selected from the group consisting of: ammonium hydroxide, sodium hydroxide, choline, tetramethylammonium hydroxide, and other quaternary ammonium compounds.

41. A method according to claim 25 wherein said base includes ammonium hydroxide in an aqueous solution in the range of approximately 5:1 to approximately 100:1 (water:ammonium hydroxide).

5 42. A method according to claim 25 wherein said oxidation agent includes hydrogen peroxide, and said base includes ammonium hydroxide.

43. A method according to claim 25 wherein said oxidation agent includes hydrogen peroxide in an aqueous solution in the range of approximately
10 5:2 to 50:1 (water:hydrogen peroxide), and said base includes ammonium hydroxide in an aqueous solution in the range of approximately 5:1 to approximately 100:1 (water:ammonium hydroxide).

44. A method according to claim 25 wherein said oxidation agent
15 includes hydrogen peroxide in an aqueous solution in the range of approximately 5:2 to 50:1 (water:hydrogen peroxide), and said base includes ammonium hydroxide in an aqueous solution in the range of approximately 5:1 to approximately 100:1 (water:ammonium hydroxide); said oxidation agent, base, and
oxide removal agent are liquids sprayed onto the surface; and further comprising
20 rotating the surface while said liquids are sprayed onto the surface.

45. A method according to claim 25 wherein said oxide removal agent includes an aqueous hydrogen halide.

25 46. A method according to claim 25 wherein said oxide removal agent includes hydrogen fluoride.

47. A method according to claim 25 wherein said oxide removal agent includes hydrogen fluoride in an aqueous solution in the range of approximately
30 10:1 to 10,000:1 (water:hydrogen fluoride).

48. A method according to claim 25 wherein said oxide removal agent includes hydrogen fluoride in an aqueous solution in the range of approximately 100:1 to 1,000:1 (water:hydrogen fluoride).

49. A method for processing a surface of semiconductor material to remove contaminants therefrom, characterized by:

repeatedly treating the surface by performing alternating growing and removing steps defined as follows:

5 growing a semiconductor oxide on the surface using a suitable oxidation agent;

 removing semiconductor oxide from the surface using an oxide removal agent;

10 said removing and growing steps being further defined by maintaining a semiconductor oxide layer upon the surface throughout the method.

50. A method according to claim 49 wherein said removing removes at least half and less than all of an oxide layer existing on the surface.

15

51. A method according to claim 49 wherein said removing removes at least two-thirds and less than all of an oxide layer existing on the surface.

52. A method according to claim 49 wherein said removing removes in
20 the range of approximately two-thirds to three-fourths of an oxide layer existing on the surface.

53. A method according to claim 49 and further comprising rotating the surface while said growing or removing steps are performed.

25

54. A method according to claim 49 and further comprising rotating the surface while liquids are sprayed onto the surface.

55. A method according to claim 49 wherein said oxidation agent and
30 oxide removal agent are liquids sprayed onto the surface.

56. A method according to claim 49 wherein said oxidation agent and oxide removal agent are liquids sprayed onto the surface; and further comprising rotating the surface while said liquids are sprayed onto the surface.

35

57. A method according to claim 49 wherein said oxidation agent and oxide removal agent are liquids sprayed onto the surface; and further comprising rotating the surface within a substantially enclosed processing chamber while said liquids are sprayed onto the surface.

5

58. A method according to claim 49 wherein said oxidation agent includes at least one constituent selected from the group consisting of hydrogen peroxide and ozone.

10

59. A method according to claim 49 wherein said oxidation agent includes at least one peroxide.

60. A method according to claim 49 wherein said oxidation agent includes hydrogen peroxide.

15

61. A method according to claim 49 wherein said oxidation agent includes hydrogen peroxide in an aqueous solution in the range of approximately 5:2 to approximately 50:1 (water:hydrogen peroxide).

20

62. A method according to claim 49 wherein said oxide removal agent includes an aqueous hydrogen halide.

63. A method according to claim 49 wherein said oxide removal agent includes hydrogen fluoride.

25

64. A method according to claim 49 wherein said oxide removal agent includes hydrogen fluoride in an aqueous solution in the range of approximately 10:1 to 10,000:1 (water:hydrogen fluoride).

30

65. A method according to claim 49 wherein said oxide removal agent includes hydrogen fluoride in an aqueous solution in the range of approximately 100:1 to 1,000:1 (water:hydrogen fluoride).

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/US 94/07943

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 H01L21/306

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 472 441 (KATO) 26 February 1992 see column 4, line 3 - line 35; figures 1-3 ---	49-52, 62-65
A	PATENT ABSTRACTS OF JAPAN vol. 11, no. 338 (E-553) 5 November 1987 & JP,A,62 118 528 (FURUTA) 29 May 1987 see abstract ---	1,2, 10-24
A	JAPANESE JOURNAL OF APPLIED PHYSICS., vol.28, no.7, July 1989, TOKYO JP pages L1274 - L1277 TAKAKUWA ET AL 'Low temperature cleaning of HF-passivated Si(111) surface with VUV light' see page L1274, right column, paragraph 2 --- -/--	25



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

20 October 1994

Date of mailing of the international search report

03. 11. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+ 31-70) 340-3016

Authorized officer

Gori, P

INTERNATIONAL SEARCH REPORT

Inter. Application No
PCT/US 94/07943

C(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	IEEE TRANSACTIONS ON SEMICONDUCTOR MANUFACTURING, vol.5, no.2, May 1992, NEW YORK US pages 114 - 120 ITANO ET AL 'Particle deposition and removal in wet cleaning processes for ULSI manufacturing' see abstract ---	11-20
A	EP,A,0 548 596 (MATSUOKA) 30 June 1993 see abstract -----	5-9, 29-33, 53-57

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No
PCT/US 94/07943

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0472441	26-02-92	JP-A- 4355921 US-A- 5229334	09-12-92 20-07-93
EP-A-0548596	30-06-93	JP-A- 5152203	18-06-93